



## Dust Air Filter, "KranCsair" , for Pre-Filtration

- Flame retardant nonwoven filter
- Application for dusty-air filtration for long life service
- Available as roll goods, shaped cut, or aluminum-framed


## Appearance of Dust Air Filter, KranCsair



WF600



WF580



WF305

## Performance Chart

Product Code	Material	Size	Thickness	Service Temp.	Flame retardancy	Re · use	Air Velocity	Pressure Loss	Efficiency	Notes
	Fiber Type	W×L (m)	(mm)	(°C)	○ = Possible	○ = Possible	(m/s)	(Pa)	(%)	
WF150	Polyester	1.6×30	7.0	≤100	○	○	2.5	29	57.0	
WF300	Polyester	1.6×30	10.0	≤100	○	○	2.5	49	72.0	
WF400	Polyester	1.6×20	13.0	≤100	○	○	2.5	59	76.0	
WF600	Polyester	1.6×20	18.0	≤100	○	○	2.5	88	82.0	
TB150	Polyolefin	1.6×30	7.0	≤80	○	○	2.5	29	57.0	
TB300	Polyolefin	1.6×30	10.0	≤80	○	○	2.5	49	72.0	
TB400	Polyolefin	1.6×20	13.0	≤80	○	○	2.5	59	76.0	
TB600	Polyolefin	1.6×20	18.0	≤80	○	○	2.5	88	82.0	
WF290	Polyester / Vinylon	1.0×100	1.0	≤100	○		2.0	18	30.0	
WF70	Polyester / Modacrylic	1.0×100	2.5	≤100	○		2.0	25	55.0	
WF3	Polyester	1.6×20	18.0	≤80	○		2.5	53	70.0	
WF50	Aramid / Polyester	1.6×20	10.0	≤180	○		1.0	20	88.0	
WF100W	Aramid / Polyester	1.6×20	18.0	≤180	○		1.0	42	90.0	
WF305	Polyester	1.6×20	20.0	≤100	○		0.5	44	98.0	
WF350	Polyester	1.6×20	20.0	≤100	○		0.5	44	98.0	oiled
WF305X	Polyester	1.6×20	20.0	≤100	○		0.5	44	98.0	
WF580	Polyester	1.6×20	20.0	≤80	○		2.5	58	84.0	
WF585	Polyester	1.6×20	20.0	≤80	○		2.5	59	85.0	oiled
FL160N	Polyester / Modacrylic	1.05×50	5.5	≤80	○	○	2.5	20	68.0	Color: black, white
FL200N	Polyester / Modacrylic	1.05×50	11.0	≤80	○	○	2.5	35	74.0	Color: black, white

[Measuring Methods]

Pressure Loss, Efficiency: In accordance with JIS9908 Type 3 (Weighing Method)

Thickness: 1.34g/cm<sup>2</sup> under load Frame Retardancy: JACA No. 11A

\* The above physical property values are typical values; they are not guaranteed values.

\* The content of the catalog is subject to change without notice.

Kurashiki Textile Manufacturing Co., Ltd.

TEL : (81)6-6261-6721 (reception)

e-mail to : info@kurasen.co.jp